

METGRIT®

BLASTING ABRASIVE

Air Blasting Abrasive

METgrit Sizes		14	18	25	40	50	80
Screen Size	Mesh No.						
0.1110	7						
0.0937	8	All Pass					
0.0787	10						
0.0661	12		All Pass				
0.0555	14						
0.0469	16	50% Min		All Pass			
0.0394	18	85% Min	75% Min		All Pass		
0.0331	20		98% Min				
0.0280	25		85% Min	70% Min		All Pass	
0.0232	30						
0.0197	35						
0.0165	40			80% Min	70% Min		All Pass
0.0138	45						
0.0117	50				80% Min	65% Min	
0.0070	80					75% Min	65% Min
0.0049	120						75% Min

CHEMICAL ANALYSIS		
Element		WT. %
Fe Total	min	94+
C	max	4.00
Mn	max	0.60
P	max	0.03
S	max	0.06

Surface cleanliness is the prime requirement for good holiday-free coating practice. METgrit's mix of hard, irregular-shaped metallic particles maximizes blast cleaning efficiency for removing paint, rust, and mill scale. The result is a cleaner surface, with high speed cleaning at a lower cost.

- * Cleaner Working Environment
- * Reduction in Generated Waste

(Average Hardness Rockwell "C" Scale 60-65)

Product performance is affected by many factors. User testing is essential to determine suitability of product for intended use. Chesapeake's SOLE Warranty is that product meets specification. Chesapeake's SOLE LIABILITY is to replace defective product. In no event shall Chesapeake be liable for consequential, indirect or other damages.

