PRODUCT DATA SHEET





Surface cleanliness is the prime requirement for good holiday-free coating practice. Engineered by combining the best steel with carbon levels high enough to be called iron. Manufactured to precise standards, quick chilled, then heat treated to produce an incredibly hard blasting material. The best abrasive for the toughest jobs. The result is a cleaner surface, with high speed cleaning at a lower cost.

- RCRA and SSPC Compliant
- Cleaner Working Environment
- Reduction in Generated Waste

CHEMICAL ANALYSIS

Fe - 97% +, C - 2.1%, Mn - <1%, P - <1%, S - <1%

| Air Blasting Abrasive Media | | | | | | |
|-----------------------------|------|----------|----------|----------|----------|----------|
| METgrit Sizes | | 25 | 40 | 40/50 | 50 | 50/80 |
| Screen | Mesh | | | | | |
| Size | No. | | | | | |
| 0.1110 | 7 | | | | | |
| 0.0937 | 8 | | | | | |
| 0.0787 | 10 | | | | | |
| 0.0661 | 12 | | | | | |
| 0.0555 | 14 | | | | | |
| 0.0469 | 16 | All Pass | | | | |
| 0.0394 | 18 | | All Pass | All Pass | | |
| 0.0331 | 20 | | | | | |
| 0.0280 | 25 | 70% Min | | | All Pass | All Pass |
| 0.0232 | 30 | | | | | |
| 0.0197 | 35 | | | | | |
| 0.0165 | 40 | 80% Min | 70% Min | | | |
| 0.0138 | 45 | | | | | |
| 0.0117 | 50 | | 80% Min | | 65% Min | |
| 0.0070 | 80 | | | 75% Min | 75% Min | |
| 0.0049 | 120 | | | | | 75% Min |